

Serial Number	Grade	Binder Content (%)	Density (g/cm ³)	Hardness (HRA)	Transverse Rupture Strength (MPa)	Grain Size (μm)
			ISO 3369	ISO 3738:1	ISO 3327	ISO 4499:2
1	ZY06-N	5.5-6.5	14.80-15.00	92.5-93.5	≥3000	≤0.8
2	ZY06-CN	7.0-8.0	13.90-14.10	92.8-94.0	≥2400	0.8-1.0
3	ZY10-CN	9.5-10.5	14.22-14.42	89.5-91.5	≥2500	1.0-1.6
4	ZY12-CN	10.5-11.5	14.10-14.30	91.0-92.5	≥3000	0.8-1.0
5	ZT30	14.5-15.5	8.90-9.10	89.0-91.0	≥1600	≤3.0